



Taimide Tech Incorporation

A High Performance Film Manufacturer

Properties of Taimide® TH Polyimide Film

Confidential

Properties	Test Items	Units	Taimide TH -025	Taimide TH -050	Taimide TH -075	Taimide TH -125	Test Condition	Test Method
	Thickness 厚度	μm	25	50	75	125	-	
Mechanical 機械特性	Tensile Strength 引張り強度	Kgf/mm ²	29	28	26	24	23°C	ASTM D882
	Elongation 抗張強度	%	92	99	98	99	23°C	ASTM D882
Electrical 電性	Volume Resistivity 体積抵抗率	Ω•cm	3.0×10^{16}	3.4×10^{16}	3.1×10^{16}	5.1×10^{16}	500V, 23°C	ASTM D257
	Surface Resistance 體積抗阻	Ω	2.8×10^{16}	3.1×10^{16}	2.7×10^{16}	8.5×10^{16}	500V, 23°C	ASTM D257
Thermal 熱性	Heat Shrinkage 表面抵抗率	%	-0.011	-0.013	-0.013	-0.018	150°C, 0.5hr	IPC TM 650
	加熱収縮率 尺寸安定性							

The above data is subject to change without notice.