



# Taimide Tech Incorporation

A High Performance Film Manufacturer

## Properties of Taimide® TX Polyimide Film

**Confidential**

Properties	Test Items	Units	Taimide TX -007	Test Condition	Test Method
	Thickness厚度	μm	7	-	
Mechanical 機械特性	Tensile Strength 引張り強度 抗張強度	Kgf/mm <sup>2</sup>	33	23°C	ASTM D882
	Elongation 伸び率 延伸率	%	52	23°C	ASTM D882
	Volume Resistivity 体積抵抗率 體積抗阻	Ω•cm	11 x 10 <sup>16</sup>	500V, 23°C	ASTM D257
Electrical 電性	Surface Resistance 表面抵抗率 表面抗阻	Ω	2.1 x 10 <sup>16</sup>	500V, 23°C	ASTM D257
	Heat Shrinkage 加熱收縮率 尺寸安定性	%	-0.008	150°C, 0.5hr	IPC TM 650

The above data is subject to change without notice.