



Taimide Tech Incorporation

A High Performance Film Manufacturer

Properties of Taimide® WB(s) Polyimide Film

Confidential

Properties	Test Items	Units	Taimide WB -012(s)	Taimide WB -025(s)	Test Condition	Test Method
	Thickness 厚度	μm	12.5	25	-	
Mechanical 機械特性	Tensile Strength 引張り強度 抗張強度	Kgf/mm ²	15	19	23°C	ASTM D882
	Elongation 伸び率 延伸率	%	43	62	23°C	ASTM D882
Electrical 電性	Volume Resistivity 体積抵抗率 體積抗阻	Ω•cm	1.1 x 10 ¹⁶	1.3 x 10 ¹⁶	500V, 23°C	ASTM D257
	Surface Resistance 表面抵抗率 表面抗阻	Ω	1.0 x 10 ¹⁶	3.4 x 10 ¹⁶	500V, 23°C	ASTM D257
Thermal 熱性	Heat Shrinkage 加熱收縮率 尺寸安定性	%	-0.016	-0.056	150°C, 0.5hr	IPC TM 650

The above data is subject to change without notice.